

HEAVY DUTY WAX™



Wax Emulsion Finish
Product #16

#1 Carnuaba Floor Wax

PRODUCT DESCRIPTION

Manufactured with pure #1 Grade Carnauba, this premium quality, self polishing emulsion floor wax dries to a tough lustrous shine which exhibits good slip resistance. Resilient enough to respond immediately to low speed dry or spray buffing techniques, traffic and scuff marks can be easily repaired, restoring the original shine. Heavy Duty Floor Wax works especially well on linoleum and rubber tile floors which respond poorly to high-speed burnishing programs. Exceptional resilience also makes it well suited for use on sealed wood floors.

APPLICATION & MAINTENANCE

Best results are obtained when the finish is applied to surfaces which are 60° F or warmer. Remove old finish or wax with one of Perma's high quality finish strippers. Mop up or vacuum the stripping solution and rinse floor thoroughly with clean water. Optimum appearance and gloss is obtained with three coats of finish. Apply thin even coats, allowing the finish to dry for approximately 30-45 minutes, depending on humidity and temperature, between coats.

Effective recoating of existing finish may be achieved by vacuuming or dry mopping the floor to remove any loose dirt or dust. Wash the floor with Tops Neutral Cleaner to remove fine dirt and soil and allow it to dry. Apply thin even coats, allowing the finish to dry for approximately 30-45 minutes between coats.

A routine maintenance program will provide the most satisfactory gloss retention and wear characteristics in any floor coating. Floor surfaces should be vacuumed or swept with a clean dry mop treated with Aqua Treat, a water based mop treatment, daily to remove abrasive loose dirt and sand. Damp mop floors with Tops Neutral Cleaner every two or three days to remove soil, salt, and film deposits which can degrade a coating's gloss. Heavy Duty Floor Wax may also be spray buffed using One Step Spray Buff and a standard speed buffer (175-300 Rpm).

SPECIFICATIONS

Nonvolatile Solids	16 ± 0.6%
Total Active	20%
pH	8.5 - 9.5
Gloss 60°	80 @ 3 coats
Color	Light Amber
Weight Per Gallon	8.4 - 8.5
Slip Resistance (ASTM)	0.55 minimum
Stability	1 year minimum at room temperature
Freeze/Thaw Stability	3 cycles minimum
Drying Time	20- 30 minutes
Water Resistance	Excellent
Gallon Coverage (Feet ²)	2000 ± 10%
Removability (Gardner)	75 cycles maximum

SAFETY INFORMATION

Health	1
Flammability	0
Reactivity	0
Personal Protection	B

This finish is not a hazardous mixture as defined in 29 CFR 1919, 1200 and M.G.L. c. 111F. Safety glasses and gloves should be worn during application and handling. If ingested, drink milk, water, or fruit juice and induce vomiting with oil of ipecac. In the event of eye contact, flush area with water for 15 minutes. **Consult with a physician.** For detailed information, consult MSDS sheet.



605 Springs Road
Bedford, MA 01730
Telephone: 978.667.5161
Fax: 978.670.5797
www.perma.com