

ONYX™

Black Urethane Modified Acrylic Sealer



Black Sealer/Finish
Product #35

PRODUCT DESCRIPTION

Onyx is a unique, black pigmented, urethane fortified, metal free, acrylic sealer/finish. Onyx is designed to provide a durable high gloss coating to a variety of surfaces including resilient tile, mineral, stone, and asphalt antifatigue floor surfaces such as those found in U.S. Postal facilities. Onyx can be used alone as a sealer and finish or top-coated with a floor finish and maintained by high speed burnishing to provide a “wet look” gloss. Onyx's inherent ultraviolet light and weather resistance also make it ideal for exterior applications such as enhancing the appearance of asphalt driveways and parking lots.

APPLICATION & MAINTENANCE

Whenever possible, remove any existing coatings. Sweep or vacuum flooring surfaces to remove gross dirt or soil. Wash the floor surface with Super Blue to remove any residual fine dirt or soil. Remove the cleaning solution with a wet vacuum or mop. Rinse the floor completely with clean water and allow it to dry. Apply the sealer in thin even coats with a clean mop or applicator. Additional coats may be applied after allowing sealer to dry for thirty to forty-five minutes. Depending on the condition of the floor, two coats generally provide the best results. To insure complete curing, allow approximately two hours between the last coat of sealer and the first coat of finish--if one is to be applied.

To remove sealer, apply Eliminator stripper at the higher recommended dilution ratio and allow the stripper to stand for approximately 10 minutes. Scrub the floor with a good quality stripping pad and a standard speed buffing machine. Removal of multiple coats of sealer may require successive stripper applications.

SPECIFICATIONS

Nonvolatile Solids	25 ± 0.6%
Total Active	31%
pH	8.2 - 9.0
Color	Black
Weight Per Gallon	8.42
Slip Resistance (ASTM)	0.55 minimum
Stability	2 years minimum at room temperature
Freeze/Thaw Stability	3 cycles minimum
Drying Time	30 - 45 minutes
Adhesion	Excellent
Water Resistance	Excellent
Gallon Coverage (Feet ²)	2000 ± 10%
Removability (Gardner)	75 cycles maximum

SAFETY INFORMATION

Health	1
Flammability	0
Reactivity	0
Personal Protection	B

This material is not a hazardous mixture as defined in 29 CFR 1919, 1200 and M.G.L. c. 111F. Safety glasses and gloves should be worn during application and handling. If ingested, drink milk, water, or fruit juice and induce vomiting with oil of ipecac. In the event of eye contact, flush area with water for 15 minutes. **Consult with a physician.** For detailed information, consult MSDS sheet.



605 Springs Road
Bedford, MA 01730
Telephone: 978.667.5161
Fax: 978.670.5797
www.perma.com