

CENTER COURT™

TM



50% Polyurethane Wood Finish

High Gloss & Durability
Product #550 @ 50%

PRODUCT DESCRIPTION

Center Court is formulated from a combination of pure oil-modified polyurethane resin, stoddard solvents, and drying and leveling agents, with no fillers or bodied vegetable additives. For use as a finish on all interior wood surfaces this premium product is easy-to-handle, exhibits superior leveling characteristics. Under normal conditions, Center Court dries at room temperature in approximately 5 hours to a hard, glossy film, which provides excellent resistance to abrasion, wearing, and chemicals. It's 50% pure polyurethane resin content provides rapid build and high gloss. Ideal for the contractor who desires outstanding results with fewer coats. This product is Federal VOC emissions law compliant.

APPLICATION & MAINTENANCE

CAUTION: If the composition or origin of an existing finish is unknown, it is strongly recommended that a test patch be applied to determine compatibility and adequate adhesion characteristics.

FLOOR PREPARATION: Sanding is advisable for new floors and old, badly worn floors. After sanding, sweep or vacuum the floor to remove wood dust and dirt, and then tack rag the floor using Waterless Cleaner.

SEALED FLOORS IN GOOD CONDITION: Clean floor thoroughly with Waterless Cleaner. Remove the soiled solution with a wet vacuum, squeegee or mop. Allow the floor to dry, then screen with an 80-100 grit screen disk. Tack rag the floor with Waterless Cleaner to remove any dirt or dust left from buffing.

APPLYING THE FINISH: Apply finish only after floor is thoroughly clean and dry. Pour finish into an applicator pan, avoiding splashing and air bubbles. Apply finish with a lamb's wool applicator, Drag/T-Bar or brush. For detailed application instructions please view Perma's interactive training video.

BUFFING BETWEEN COATS: Screen between coats with a 120 grit or finer screen to ensure adhesion and to remove raised grains in wood and provide a smoother finished appearance. Sweep or vacuum the floor to remove loose fibers, steel wool particles, or dirt. Apply markings, allow to dry and screen. Apply the second coat and buff when dry if desired. Sweep or vacuum carefully, and apply a third coat if required.

SPECIFICATIONS

Color	1 - 3 / Gardner
Solids	50%
Weight Per Gallon	7.5
Hardness	40 / Sward
Viscosity	95 CPS
Solvents	Mineral Spirits
Flash Point	105°F minimum
Dry Time	Tack free-5 hours
Water Resistant	24 hours-No effect
Alcohol	1 hour-No effect
Gasoline	24 hours-No effect
Caustic 5%	2 hours-No effect
Soap Resistance	24 hours-No effect
Slip Resistance	(ASTM F-609) 0.5 Minimum
Coverage	400 - 600 Ft. ² /Gallon
VOC	<450 grams/liter

SAFETY INFORMATION

Health	1
Flammability	2
Reactivity	0
Personal Protection	B
WARNING: Harmful if swallowed or inhaled! COMBUSTIBLE, Flash Pt. 40oC (105oF). Long term exposure may cause lung damage. Contains Stoddard Solvent CAS #8052-41-3. Avoid breathing vapors or mist. Use with adequate ventilation. Keep away from heat and flame. Keep container closed. For complete information consult MSDS sheet. Dispose of empty containers safely. For professional use only. Keep out of reach of children. Possible Organ Effects: Eyes, Respiratory System, Skin.	

